



NAYARA

CHEMISTRY THAT PERFORMS

H120IG

Provisional

POLYPROPYLENE HOMOPOLYMER FOR INJECTION MOULDING APPLICATIONS

Nayara H120IG is Polypropylene Homopolymer made with Unipol technology using state of the art catalyst system. The grade is designed for general purpose injection moulding applications. The articles made from H120IG exhibit high stiffness and very good dimensional stability.

APPLICATIONS

General purpose injection moulded articles, as a blending component in furniture / automotive compounds, general purpose containers for food / pharma packaging, household articles etc.

ADDITIVES

- Thermal Stabilizer
- Anti-Static Agent

TYPICAL PROPERTIES

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
Resin Properties			
Melt Flow Rate (230° C. /2.16 Kg)	g/10 min.	ASTM D1238	12.0
Density @ 23° C.	g/cc	ASTM D792	0.900 – 0.910
Mechanical Properties			
Tensile Yield Strength	MPa	ASTM D638	36.0
Elongation at Yield	%	ASTM D638	7.0
Flexural Modulus (1 % Secant)	MPa	ASTM D790A	1550
Izod Impact Strength	J/m	ASTM D256	30
Hardness	Shore D	ASTM D2240	70
Thermal Properties			
DSC Melting Point	° C	ASTM D3418	160 - 165
Heat Deflection Temperature (0.45 MPa)	° C	ASTM D648	104

Note: All the properties mentioned above are typical properties and not to be considered as specifications. All the mechanical properties are determined on ASTM D638 Type I specimen when molded according to ASTM D4101.

Nayara Energy Limited

5th Floor, Jet Airways Godrej BKC, Plot No. C-68, G Block, Bandra Kurla Complex, Bandra (E), Mumbai 400051

T +91 22 6612 1800 | Website: www.nayaraenergy.com

Registered. Office: Khambhalia, Post box no. 24, Dist. Devbhumi, Dwarka, Gujrat 361305; T +91 2833 661444



NAYARA

CHEMISTRY THAT **PERFORMS**

Typical Processing Guidelines:

Processing temperature: 210 – 260° C

Mold temperature: 20 – 50° C

Note: The processing conditions mentioned above are for reference only. The conditions may vary based on the machine used and product to be manufactured.

Regulatory Compliance:

For regulatory compliance information of the grade, please contact Nayara Energy representative.

Storage:

Bags containing Nayara polymer products, should be stored in a covered dry place away from heat and sun rays. Recommended storage temperature is below 50° C.

Disclaimer

The information provided in this technical data sheet is true to the best of our knowledge. The data provided in the document is for reference only and the values stated are typical values obtained when the polymer is processed under standard processing conditions and when tested as per stated test standards. Nayara energy do not guarantee or warrant the performance of the end product made from this grade. It is sole responsibility of the user to ascertain the suitability of the grade for intended application and process. User is advised to test the properties of the end product and to satisfy itself regarding performance. Nayara energy will not be responsible for any direct or indirect loss or damage or injury because of the use of this grade or information of the grade given in this document. This document is not a suggestion to use our grade. Nayara energy reserves the right to change the information presented in this document any time without any prior intimation.

Nayara Energy Limited

5th Floor, Jet Airways Godrej BKC, Plot No. C-68, G Block, Bandra Kurla Complex, Bandra (E), Mumbai 400051

T +91 22 6612 1800 | Website: www.nayaraenergy.com

Registered. Office: Khambhaliya, Post box no. 24, Dist. Devbhumi, Dwarka, Gujrat 361305; T +91 2833 661444