



H030TN

POLYPROPYLENE HOMOPOLYMER FOR SHEET EXTRUSION & THERMOFORMING

Nayara H030TN is polypropylene Homopolymer made with Unipol technology using state of the art catalyst system. The grade architecture provides higher melt strength required during thermoforming operation. The grade is nucleated and hence helps in achieving lower cycle times in molding operation as well as better clarity and higher gloss in the end product.

APPLICATIONS

Sheets for thermoformed cups & containers, Rigid packaging, Sheets for folded articles like packaging boxes.

TYPICAL PROPERTIES

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
Resin Properties			
Melt Flow Rate (230/2.16 Kg)	g/10 min.	ASTM D1238	3.0
Mechanical Properties			
Tensile Yield Strength	MPa	ASTM D638	37.0
Elongation at Yield	%	ASTM D638	6.0
Flexural Modulus (1 % Secant)	MPa	ASTM D790A	1850
Izod Impact Strength	J/m	ASTM D256	60
Hardness	Shore D	ASTM D2240	70
Thermal Properties			
DSC Melting Point	°C	ASTM D3418	160 - 165
Heat Deflection Temperature (0.45 MPa)	°C	ASTM D648	95

Note: All the properties mentioned above are typical properties and not to be considered as specifications. All the mechanical properties on ASTM D638 Type I specimen when molded according to ASTM D4101.

DISCLAIMER

The information provided in this technical data sheet is true to the best of our knowledge. The data provided in the document is for reference only. Nayara energy do not guarantee or warrant the performance of the end product made from this grade. It is sole responsibility of the user to ascertain the suitability of the grade for intended application and process. This document is not a suggestion to use our grade.

Nayara Energy Limited

5th Floor, Jet Airways Godrej BKC, Plot No.C-68, G Block, Bandra Kurla Complex, Bandra (E), Mumbai 400051

T +91 22 6612 1800 | Website: www.nayaraenergy.com

Registered. Office: Khambhalia, Post box no. 24, Dist. Devbhumi, Dwarka, Gujarat 361305; T +91 2833 661444



NAYARA
ENERGY