



CHEMISTRY THAT PERFORMS

H036RG

POLYPROPYLENE HOMOPOLYMER FOR RAFFIA TAPES & SHEET APPLICATION

Nayara H036RG is Polypropylene Homopolymer made with Unipol technology using state of the art catalyst system. The grade is designed for high line speed, high throughput raffia extrusion lines without compromising on mechanicals. The superior catalyst technology and special additives used in making this grade allows smooth processing with low water carry over at higher throughputs without any breaks to produce high tenacity tapes used for making woven sacks.

APPLICATIONS

Woven sacks for fertilizer, cement, polymer packaging; Leno bags for packaging of agricultural produce, wrapping fabric, FIBC, monofilaments, ropes, sheets for thermoforming.

ADDITIVES

- Thermal Stabilizer

TYPICAL PROPERTIES

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
Resin Properties			
Melt Flow Rate (230° C. /2.16 Kg)	g/10 min.	ASTM D1238	3.6
Density @ 23° C	g/cc	ASTM D792	0.900 – 0.910
Mechanical Properties			
Tensile Yield Strength	MPa	ASTM D638	37.0
Elongation at Yield	%	ASTM D638	8.0
Flexural Modulus (1 % Secant)	MPa	ASTM D790A	1600
Izod Impact Strength	J/m	ASTM D256	40
Hardness	Shore D	ASTM D2240	70
Thermal Properties			
DSC Melting Point	° C	ASTM D3418	160 - 165
Heat Deflection Temperature (0.45 MPa)	° C	ASTM D648	104

Note: All the properties mentioned above are typical properties and not to be considered as specifications. All the mechanical properties on ASTM D638 Type I specimen when molded according to ASTM D4101.

Nayara Energy Limited

5th Floor, Jet Airways Godrej BKC, Plot No. C-68, G Block, Bandra Kurla Complex, Bandra (E), Mumbai 400051

T +91 22 6612 1800 | Website: www.nayaraenergy.com

Registered. Office: Khambhalia, Post box no. 24, Dist. Devbhumi, Dwarka, Gujarat 361305; T +91 2833 661444

Updated as on May 2025



CHEMISTRY THAT PERFORMS

Typical Processing Guidelines:

Processing temperature: 210 – 265° C

Water bath temperature: 30 – 50° C

Stretching temperatures: 130 – 160° C (depending on type of hardware)

Note: The processing conditions mentioned above are for reference only. The conditions may vary based on the machine used and product to be manufactured.

Regulatory Compliance:

The product complies with the requirements of,

(1) IS 10910:1984: Specification for Polypropylene & its Copolymers for safe use in contact with Foodstuff, Pharmaceutical & Drinking Water.

(2) IS 16738: 2001: The additives in the grade formulation comply to the “Positive List of Constituents of Polypropylene and its Copolymers in Contact with. Foodstuffs, Pharmaceuticals and Drinking Water”.

(3) FDA: CFR Title 21, 177.1520: Grade meets the requirements of the US FDA specifications and limitations in 21 CFR 177.1520 regarding safe use of articles or components of articles of olefin polymers intended for use in contact with food.

EPR compliance: The product is not to be used in the manufacture of single use plastic items prohibited under the Plastic Waste Management Rules, 2016 including plastic sheets < 50 micron thickness, non-woven carry bags < 60 GSM, Carry bags < 120 micron thickness.

Storage:

Bags containing Nayara polymer products, should be stored in a covered dry place away from heat and sun rays. Recommended storage temperature is below 50° C.

Disclaimer

The information provided in this technical data sheet is true to the best of our knowledge. The data provided in the document is for reference only and the values stated are typical values obtained when the polymer is processed under standard processing conditions and when tested as per stated test standards. Nayara energy do not guarantee or warrant the performance of the end product made from this grade. It is sole responsibility of the user to ascertain the suitability of the grade for intended application and process. User is advised to test the properties of the end product and to satisfy itself regarding performance. Nayara energy will not be responsible for any direct or indirect loss or damage or injury because of the use of this grade or information of the grade given in this document. This document is not a suggestion to use our grade. Nayara energy reserves the right to change the information presented in this document any time without any prior intimation.

Nayara Energy Limited

5th Floor, Jet Airways Godrej BKC, Plot No. C-68, G Block, Bandra Kurla Complex, Bandra (E), Mumbai 400051
T +91 22 6612 1800 | Website: www.nayaraenergy.com

Registered. Office: Khambhalia, Post box no. 24, Dist. Devbhumi, Dwarka, Gujrat 361305; T +91 2833 661444

Updated as on May 2025